

Technical Data Sheet

Quick Dry Rubberized Undercoat is a rapid-drying highly protective automotive coating for autobody interiors, underhood and underbody applications. Resists abrasion and inhibits rust as it seals out dust and moisture. Deadens sound. Excellent adhesion to painted and unpainted surfaces.

SUITABLE SUBSTRATES

Substrate		Substrate		Substrate	
Painted or Primed Steel	✓	Galvanized Steel	✓	Painted or Primed Aluminum	✓
Bare Steel	✓	Bare Aluminum	✓		

MIXING



Mix Ratio: Ready to Spray

Pot Life: N/A

SURFACE PREPARATION



Clean with SCAT 6311, Speedi SCAT 6321 or Aqua SCAT 2 1391/1394.

APPLICATION



AEROSOL:

Shake well. Wash and solvent clean surface to remove all rust, dirt and grease using SCAT 6311, Speedi SCAT 6321 or Aqua SCAT 2 1391/1394. Hold can in an upright position and spray 8-10 inches from surface, using steady light strokes. 2 coats (@2.5-3.5 mils per coat) will produce a better finish than one heavy coat. Remove overspray with Acry Solvent 9783/9784.



QUART/GALLON:

Stir thoroughly before use. Wash and solvent clean surface to remove all rust, dirt and grease. Apply with a shutz gun, using the gun manufacturer's recommended air pressure. Allow 15 - 20 minutes between coats. Thoroughly clean spray gun with Acry Solvent 9783/9784 immediately after use. Max temperature resistance is 250°F (121°C).

NOTE: Topcoating is not recommended. This product contains asphalt which may stain light colored topcoats.

PRODUCT SPECIFICATIONS

Color: Black	Shelf Life: 1 year
Size: Gallon (4361-F), Quart (4364-F), 24 oz Aero (4363-F)	

REGULATORY:

Category: Underbody Coating	4361-F/4364-F	Category: Undercoating	4363-F
VOC Actual	2.74#/gal (328 g/l)	VOC Content	<40% by weight
VOC Regulatory	3.58#/gal (429 g/l)		
Weight % of Volatiles	55.78		
Weight % of Water	0.1		
Weight % of Exempt Compounds	20.08		
Volume % of Exempt Compounds	23.35		
Density of Material #/gal	7.69		

LIMITATIONS & PRECAUTIONS

- This product provides adhesion & corrosion protection when used over noted (checked) substrates - when properly cleaned, sanded & applied.
- Visit www.tat-co.com to assure use of the most current instructions and TDS on this product.
- See website (www.tat-co.com) for this document in other languages. (Vea el web site para este documento en español. Voir le site web pour ce document en français.)
- For use only by professional, trained painters. Not for sale to or use by the general public.
- Before use, read and follow all TDS, label and SDS precautions.
- All Standard Operating Procedures (SOP) can be found on the Transtar website at www.tat-co.com.

Visit www.tat-co.com to assure you are using most updated TDS, to view in other languages and for links to Standard Operating Procedures (SOPs).

TRANSTAR AUTOBODY TECHNOLOGIES • 2040 HEISERMAN DRIVE, BRIGHTON, MI 48114 • (800) 824-2843

FAX (800) 477-7923 • EMAIL: info@tat-co.com